

# **TEST REPORT**

## **REPORT NUMBER**

170601007SHF-BP-2

## **ISSUE DATE**


2022/8/17

## **PAGES**

4

## **DOCUMENT CONTROL NUMBER**

LFT-APAC-SHF-OP-10a © 2022 INTERTEK





Intertek Testing Services Ltd., Shanghai No.7 Building, No. 6958 Daye Road, Fengxian District, Shanghai, China Tel: 021-61136116 Fax: 021-61189921

Website: www.intertek.com

# **Test Report**

Issue Date: 2022/8/17 Intertek Report No. 170601007SHF-BP-2

Applicant: Wood plastic board

Applicant Address: Dongguan City, Guangdong Province

Attn: Huang

**SUBJECT:** Performance testing

Co-Ex Decking A

Dear Sir,

This test report for represents the results of our evaluation of the above referenced product(s) to the requirements contained in the following standards:

#### **TEST METHODS AND STANDARDS**

Refer to the next following Pages.

SAMPLE ID	MODEL	SPECIFICATI ON
S170601007SHF.0 01	140×23	/

SAMPLE RECEIEVED: 2022/6/02

TESTED FROM: 2022/8/12 T

0

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.



Issue Date: 2022/8/17 Intertek Report No. 170601007SHF-BP-2

## Test Items, Method and Results:

EN 15534-4: 2014 Composites made from cellulose-based materials and thermoplastics (usually called wood-polymer composites (WPC) or natural fibre composites (NFC)) Part 4: Specifications for decking profiles and tiles

Indenter: a hardened steel spherical body with diameter of 10 mm

Test load: Additional load of 2000N with preload of 20N

Indentation time:  $(25 \pm 5)$  s Recovery time: at least 24h

Test Sample	Test Items	Test Method	Test Results
Co-Ex Decking A	Resistance to indentatio n	EN 15534-1:2014 Section 7.5 EN 15534-4:2014 Section 4.5.7	Brinell hardness: 79 MPa Rate of elastic recovery: 54%



Issue Date: 2022/8/17 Intertek Report No. 170601007SHF-BP-2

**APPENDIX: SAMPLE RECEIVED PHOTO** 



## **REPORT AUTHORIZED**

When signed with physical or electronic signature, the contents of this report have been prepared and approved per Intertek's quality process in accordance with ISO 17025.

Name: Sun Sun

Title: Approver

Daniel Zhang

Title: Reviewer

Name: Torres Qi

Title: Project Engineer

## **Revision:**

NO.	DATE	CHANGES	AUTHOR	REVIEWER
170601007SHF-BP	2022/8	First issue	Torres Qi	Daniel
-2	/17			Zhang



# **TEST REPORT**

## **REPORT NUMBER**

170601007SHF-BP-3

## **ISSUE DATE**


2022/8/17

## **PAGES**

4

## **DOCUMENT CONTROL NUMBER**

LFT-APAC-SHF-OP-10a © 2022 INTERTEK





Intertek Testing Services Ltd., Shanghai No.7 Building, No. 6958 Daye Road, Fengxian District, Shanghai, China Tel: 021-61136116 Fax: 021-61189921

Website: www.intertek.com

# **Test Report**

Intertek Report No. 170601007SHF-BP-3 Issue Date: 2022/8/17

Applicant: Wood plastic board

**Applicant Address:** Dongguan City, Guangdong Province

Attn: Xuemei Huang

**SUBJECT:** Performance testing

Co-Ex Decking A

Dear Sir,

This test report for represents the results of our evaluation of the above referenced product(s) to the requirements contained in the following standards:

#### **TEST METHODS AND STANDARDS**

Refer to the next following Pages.

SAMPLE ID	MODEL	SPECIFICATI ON
S170601007SHF.0 02	140×23	/

SAMPLE RECEIEVED: 2022/6/23

TESTED FROM: 2022/8/17 Т

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

LFT-APAC-SHF-OP-10a Version: 1-September-2022



Issue Date: 2022/8/17 Intertek Report No. 170601007SHF-BP-3

## Test Items, Method and Results:

Test Sample	Test Items	Test Method	Test Results
Co-Ex Decking A	Abrasion Resistance	ASTM D4060-14	Mass loss: 30.0 mgWear index: 30

Note:

1. Type of Wheel: CS-17

2. Load on each Wheel: 1000 g

3. Revolutions: 1000



Issue Date: 2022/8/17 Intertek Report No. 170601007SHF-BP-3

**APPENDIX: SAMPLE RECEIVED PHOTO** 



## **REPORT AUTHORIZED**

When signed with physical or electronic signature, the contents of this report have been prepared and approved per Intertek's quality process in accordance with ISO 17025.

Name: Sun Sun

Title: Approver

检验检测专用章Name: Daniel Zhang

Title: Reviewer

Name: Torres Qi Title: Project Engineer

## **Revision:**

NO.	DATE	CHANGES	AUTHOR	REVIEWER
170601007SHF-BP	2022/8	First issue	Torres Qi	Daniel
-3	/17			Zhang



# **TEST REPORT**

#### **REPORT NUMBER**

170601007SHF-BP-0

## **ISSUE DATE**


2022/8/17

## **PAGES**

5

## **DOCUMENT CONTROL NUMBER**

LFT-APAC-SHF-OP-10a © 2022 INTERTEK





Intertek Testing Services Ltd., Shanghai No.7 Building, No. 6958 Daye Road, Fengxian District, Shanghai, China Tel: 021-61136116 Fax: 021-61189921

Website: www.intertek.com

## **Test Report**

Intertek Report No. 170601007SHF-BP-0 Issue Date: 2022/8/17

Applicant: Wood plastic board

Applicant Address: Dongguan City, Guangdong Province

Attn: Xuemei Huang

**SUBJECT:** Performance testing

Co-Ex Decking C

Dear Sir,

This test report for represents the results of our evaluation of the above referenced product(s) to the requirements contained in the following standards:

#### **TEST METHODS AND STANDARDS**

Refer to the next following Pages.

SAMPLE ID	MODEL	SPECIFICATI ON
S170601007SHF.0 05	140×23	/

SAMPLE RECEIEVED: 2022/6/02

TESTED FROM: 2022/8/11 Т

This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program.

LFT-APAC-SHF-OP-10a Version: 1-September-2022



Issue Date: 2022/8/17 Intertek Report No. 170601007SHF-BP-0

#### Test Items, Method and Results:

Test Item: Resistance to artificial weathering

Test Sample: Co-Ex Decking C

Test Method: ISO 4892-2:2013 cycle 1

The Exposure cycle:

1) 102 min light at  $(65\pm3)^{\circ}$ C, Black-standard-temperature, Chamber temperature 38  $\pm$  3 °C, Relative humidity  $(50\pm10)\%$ , Irradiance:  $0.51\pm0.02~\text{W/(m}^2\cdot\text{nm})$  at 340 nm Narrowband

2) 18 min light and water spray, Irradiance: 0.51 ± 0.02 W/(m<sup>2</sup>·nm) at 340 nm Narrowband

#### Test Result:

Exposure time	ΔL*	Δa*	Δb*	ΔΕ*	Grey scale	Observation
720 hours	-0.22	0.08	0.09	0.26	5	Part showed no color change
1440 hours	-0.30	0.10	0.21	0.40	4-5	Part showed slight color change
2000 hours	-0.35	0.11	0.21	0.43	4-5	Part showed slight color change

#### Note:


1. Test photos were shown in next page



Issue Date: 2022/8/17 Intertek Report No. 170601007SHF-BP-0

## **Test Photos:**







After 1440 hours test



After 2000 hours test



Issue Date: Intertek Report No. 170601007SHF-BP-0 2022/8/17

**APPENDIX: SAMPLE RECEIVED PHOTO** 



## **REPORT AUTHORIZED**

When signed with physical or electronic signature, the contents of this report have been prepared and approved per Intertek's quality process in accordance with ISO 17025.

Sun Sun Name:

Title: Approver

Daniel Zhang

title: Reviewer

Name:

Name: Torres Qi

Ri

Title: Project Engineer

## **Revision:**

NO.	DATE	CHANGES	AUTHOR	REVIEWER
170601007SHF-BP	2022/8	First issue	Torres Qi	Daniel
-6	/17			Zhang